



Physical Properties	Specifications
Substrate	Acrylic
Substrate Colours	Black, White, Transparent, Blue and Red
Substrate Gauges	0.020 mils
Sheet Sizes	24.25" x 49"
Fabrication Properties	Router, saw, die-cut and laser
UV Light Resistance	Not applicable
Abrasion	Taber testing < 200 cycles with CS17 wheel/500 grams
Cleaning Instructions	Not applicable
Optical	Not applicable
Vicat Softening Temperature	ASTM D-1525 227 degrees F
Specific Gravity	ASTM D-792 1.16
Tensile Modulus	ASTM D-638 255,000 p.s.i.
Izod Impact Strength	ASTM D-256 @ 73 F 1.20 ft-lbs/in notch
Temperature Range in Continual Use	ASTM D-3418 150–170 degrees F
Tensile Elongation at Break	ASTM D-638 38%
Tensile Strength @ Maximum	ASTM D-638 6,500 p.s.i.
Flexural Strength @ Maximum	ASTM D-790 8,890 p.s.i.
Heat Deflection Temperature	ASTM D-648 (@ 264 p.s.i.; annealed) 176 degrees F
Hardness	ASTM D-785 40M Rockwell
Glass Transition Temperature Tg	ASTM D-3418 226 degrees F

All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses, and that purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. THERE IS NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR ANY PURPOSE. PRODUCTS WILL MEET SELLER'S STANDARD SPECIFICATIONS THEREFORE, BUT THERE ARE NO OTHER WARRANTIES FOR THE PRODUCTS DESCRIBED.